

AMENDMENTS TO THE SPECIFICATION:

Please add the following new paragraph after the paragraph beginning on page 3, line 27 and ending on page 4, line 16:

Pyrex[®] glass typically comprises, by weight, about 81% SiO₂, about 13% B₂O₃, about 4% Na₂O and about 2% Al₂O₃.